

# R-SL-MAGK Acrylic for Drywall

Flexible acrylic dispersion sealant.

## Product information



## Applications

- Filling of joints and corner joints in the connections between gypsum and cardboard and similar finishing materials in drywall systems.
- Grouting of joints between walls and floor tiles, baseboards, ceiling moldings, suspended ceilings and parapets.
- Connections between panels and frames, masking strips and joinery.
- Filling of the gaps inside the buildings, scratches, cracks in gypsum plaster, gypsum blocks and precasts of similar type.

## Features and benefits

- For joining of plasterboard sheets in attics.
- Solvent-free
- Flexible plastic joint, water-resistant after curing.
- Can be painted when fully-cured.
- Suitable for most construction substrates.
- Designed for internal and external use, with resistance to changeable weather conditions, once cured.

## Base materials

### Approved for use in:

- Plasterboard
- Metal Sheet & Profiles
- Ceramics
- Concrete
- Masonry
- Wood
- Glass
- High-Density Natural Stone
- Plaster

## Installation guide



1. Clean up the gap. Surface, that the acrylic will be applied on, should be clean, free of dust, dirt, grease, oil, rust, remains of old sealant and other substances that might lower the cohesion.
2. In case of absorptive substrates, the priming is suggested. The test of adhesion prior application is also recommended.
3. Prior to application, protect edges with masking tape
4. Cut the tip of the cartridge, leaving part of the thread. Screw the applicator on to the thread, then cut at the required angle to give an aperture width suited to the joint.
5. Use manual or pneumatic gun applicator.
6. The applied acrylic can be smoothed with a spatula.
7. After completing the application, wipe tools with a paper towel and wash with water.
8. Fully dried product should be secured with plaster, paint etc.

## Technical Data

Parameter		Value	Methods
Application temperature	[°C]	+10 ÷ +30	
Coverage	-	18 linear meters of 4x4 mm joint per one 300 ml cartridge	
Thermal resistance (upon hardening)	[°C]	-30 ÷ +70	
Skin formation time	[min]	20	
Pretreatment time	[min]	20	
Drying time	[day]	max. 5	
Hardening system	-	one-component-water evaporation	
Density	[kg/dm <sup>3</sup> ]	1,5	
Shore A hardness	-	40	
Ultimate elongation	[%]	>25	
Shrinkage	[%]	15	
Allowable deformation	[%]	7,5	
<b>R-SL-MAGK-02</b>			
Colour	-	white	
Packaging	-	300 ml cartridge	

Parameter		Value
Storage temperature	[°C]	+10 ÷ +25
Shelf life	-	up to 12 months in closed containers
Comments	-	Store in cool and dry conditions in well ventilated room.

## Product commercial data

Product Code	Colour	Quantity [pcs]			Weight [kg]			Bar Codes
		Box	Outer	Pallet	Box	Outer	Pallet	
R-SL-MAGK-02	white	15	15	1260	8.3	8.3	726.8	5905907912423