

RPP-45 Polyurethane Gun Foam

Low-pressure, one-component polyurethane foam with applicator gun.

Product information



Applications

- Fixing pipes and cables in HVAC systems
- The application of PU foam: installation of windows and doors, filling, sealing, insulation in the construction industry
- · Installation of windows and door
- Easy fixing of door and window frames timber, metal or PVC
- Ideal for mounting, sealing and sound proofing
- · Filling empty spaces, cracks, pipe passages
- Filling gaps in the thermal and acoustic insulation
- · Fixing (for installation of doors and windows)
- Thermal insulation of roofing (including flat roofs)

Features and benefits

- · Suitable for use indoors and outdoors.
- Excellent sound and thermal insulation properties.
- Can be painted or plastered when cured
- · Cutting time 40 min after apllication
- Yield up to 45 l
- Resistant to mould and fungi.
- Excellent adhesion to most materials and substrates used in construction.

Base materials

Approved for use in:

- Concrete
- Masonry
- Wood
- Metal Sheet & Profiles
- PVC Profile
- · Window Profile





Installation guide















- 1. Wear protective gloves. Ensure surfaces are free from dust, dirt or debris.
- 2. Before using, make sure that the can temperature is above zero (optimum $+20^{\circ}$ C). Application temperature from $+5^{\circ}$ C up to $+30^{\circ}$ C.
- 3. Shake can vigorously for 30 seconds to mix properly components.
- 4. Screw gun onto the can. Hold can upside-down during application.
- 5. Moisten surfaces with water prior to application.
- 6. Fill gaps from down to up, zigzag motion, alternating from one wall to the other. Fill gaps to approximately 60 % volume. Max. wide of the gap 3-4 cm. Wider gaps should be applied after hardening of the previous layer. Each layer should be moistened with water using a spray.
- 7. After full curing, cut the excess foam with a knife and protect it from UV exposure by coating with plaster, paint, acrylic or silicone.
- 8. In the event of a stoppage exceeding five minutes duration, wipe the nozzle with cleaner for foam applicator.
- 9. After removing the applicator gun from the can, wipe down the nozzle and gun (internal and external surfaces) using a cleaner.

Technical Data

Parameter		Value	Methods		
Application temperature	[°C]	+5 ÷ +30			
Can temperature	[°C]	+20			
Efficiency	[dm³]	max. 45			
Colour	-	Light yellow			
Post-expansion	[%]	120			
Skin formation time	[min]	4÷7	20°C, RH 90%		
Pretreatment time	[min]	45	20°C, RH 90%		
Complete hardening time	[h]	24			
Fire resistance class	-	B3	DIN 4102		
Density	[kg/m ³]	19 ± 10	PN-EN ISO 845:2000		
Dimensional stability	[%]	≤3	40°C, RH 95%, 24 hrs		
Water absorption after 24h	[kg/m³]	≤1	PN-EN 1609:1999		
Tensile strength	[kPa]	≥ 100	PN-EN 1607:1999		
Compressive strength	[kPa]	≥ 40	PN-EN 826:1998		
Thermal resistance (upon hardening)	[°C]	-50 ÷ +90			
Thermal conductivity	[W/mK]	0,038			
Preparations solublity	-	Acetone, before hardening	Cleaner RPC-0500		
Soundproofing coefficient	[dB]	61	EN 12354-3		
Volume	[ml]	750			

Parameter		Value		
Shelf life [month]		15		
		upright position in an originally closed container		
	-	the storage temperature: from +5°C to +35°C (room temperature is recommended)		
rage conditions		dry, cool and well-ventilated place away from direct sunlight and other sources heat and ignition		
		storing the product in conditions other than recommended may shorten the life time even by 3 months		

Product commercial data

Product Code Colour	Volume [ml]	Quantity [pcs]			Weight [kg]			Bar Codes	
	Cotour	Cotodi Votalile [liit]	Вох	Outer	Pallet	Вох	Outer	Pallet	Bai Codes
RPP-45	Light yellow	750	12	12	672	10.9	10.9	638.6	5906675151120