

## RPP-65-W High Yield Polyurethane Gun Foam - Winter version

Highly efficient, low-pressure, one-component polyurethane foam with applicator gun - Winter version.

### Product information



### Applications

- Fixing pipes and cables in HVAC systems
- The application of PU foam: installation of windows and doors, filling, sealing, insulation in the construction industry
- Installation of windows and door
- Easy fixing of door and window frames - timber, metal or PVC
- Sealing during installation works
- Thermal and acoustic insulation
- Filling empty spaces, cracks, pipe and cable passages
- Fixing (for installation of doors and windows)
- Setting stairs and other elements of the construction works
- Filling frame structures

### Features and benefits

- High yield - up to 65 l from one can
- Flexibility and dimensional stability - does not deform window and door frames
- Ideal for frame construction works
- Great structure - excellent insulation properties
- Good mechanical strength and adhesion to typical construction materials
- Excellent sound and thermal insulation properties.

### Base materials

#### Approved for use in:

- Concrete
- Masonry
- Wood
- Metal Sheet & Profiles
- PVC Profile
- Window Profile

### Installation guide



1. Wear protective gloves. Ensure surfaces are free from dust, dirt or debris.
2. Remove the frost from the working surface.
3. Before using, make sure that the can temperature is above zero (optimum +20°C). Application temperature from -10°C up to +30°C.
4. Shake can vigorously for 30 seconds to mix properly components.
5. Screw gun onto the can. Hold can upside-down during application.
6. Fill gaps from down to up, zigzag motion, alternating from one wall to the other. Fill gaps to approximately 60 % volume. Max. wide of the gap 3-4 cm. Wider gaps should be applied after hardening of the previous layer.
7. After full curing, cut the excess foam with a knife and protect it from UV exposure by coating with plaster, paint, acrylic or silicone.
8. In the event of a stoppage exceeding five minutes duration, wipe the nozzle with cleaner for foam applicator.
9. After removing the applicator gun from the can, wipe down the nozzle and gun (internal and external surfaces) using a cleaner.

## Technical Data

Parameter		Value	Methods
Efficiency	[dm <sup>3</sup> ]	max. 65	
Application temperature	[°C]	-10 ÷ +30	
Can temperature	[°C]	+20	
Colour	-	Light yellow	
Post-expansion	[%]	120	
Skin formation time	[min]	4 ÷ 8	20°C, RH 90%
Pretreatment time	[min]	40	20°C, RH 90%
Complete hardening time	[h]	24	
Fire resistance class	-	B3	DIN 4102
Density	[kg/m <sup>3</sup> ]	22 ± 10	PN-EN ISO 845:2000
Dimensional stability	[%]	≤5	40°C, RH 95%, 24 hrs
Water absorption after 24h	[kg/m <sup>3</sup> ]	≤2	PN-EN 1609:1999
Tensile strength	[kPa]	≥ 100	PN-EN 1607:1999
Compressive strength	[kPa]	≥ 50	PN-EN 826:1998
Thermal resistance (upon hardening)	[°C]	-50 ÷ +90	
Thermal conductivity	[W/mK]	0,036	
Preparations solubility	-	Acetone, before hardening	Cleaner RPC-0500
Soundproofing coefficient	[dB]	61	EN 12354-3
Volume	[ml]	840	

Parameter		Value
Shelf life	[month]	15
Storage conditions	-	<p>upright position in an originally closed container</p> <p>the storage temperature: from +5°C to +35°C (room temperature is recommended)</p> <p>dry, cool and well-ventilated place away from direct sunlight and other sources of heat and ignition</p> <p>storing the product in conditions other than recommended may shorten the life time even by 3 months</p>

## Product commercial data

Product Code	Colour	Volume [ml]	Quantity [pcs]			Weight [kg]			Bar Codes
			Box	Outer	Pallet	Box	Outer	Pallet	
RPP-65-W	Light yellow	840	12	12	672	12.6	12.6	734.9	5906675159768